

Symbol	CVE
Backing	Polyester Film / Glass Filament
Backing Thickness	5.5 mil (0.140 mm)
Color	Transparent
Adhesive	Acrylic
Total Thickness	6.5 mil (0.165 mm)
Dielectric Strength	5000 Volts
Dielectric Constant	1.82
Temp/Class	155°C / F
Insulation Resistance	10 ⁴ megohms
Tensile Strength	250 lbs/in (438N/cm)
Adhesion to Steel	40 oz/in (4.4N/cm)
Elongation	5 %
Electrolytic Corrosion	1.0 Direct/ A, 1*
Flammability	BU 2*
Storage Stability	Excellent
Solvent Resistance	Excellent
Moisture Resistance	Excellent
UL File #	E20780
CSA File	LR94980
Standardowe szerokości*	6, 9, 12, 19, 25, 30 mm

* istnieje możliwość przygotowania taśm o wymiarach według potrzeb Klienta.

Data modyfikacji: 08-07-2020

Taśmy należy przechowywać w zamkniętych kartonach, w pomieszczeniu o temperaturze pokojowej. Optymalne przyleganie do podłoża uzyskamy na powierzchni czystej, suchej i odtłuszczonej.

Wszystkie informacje, dane techniczne oraz zalecenia odnoszące się do produktów oferowanych przez naszą firmę, oparte są na testach, które oceniamy jako wiarygodne; ze względu jednak na różnorodność materiałów, podłoży i odmiennych warunków pracy nie możemy zagwarantować całkowitej skuteczności aplikacji. Użytkownik ponosi całkowitą odpowiedzialność za decyzję czy dany produkt jest odpowiedni do zastosowania przy konkretnej aplikacji oraz za jej wykonanie.